



TITAN PETCHEM (M) SDN. BHD.

(Co. No. 154990 W)
(Formerly known as Titan PP Polymers (M) Sdn. Bhd.)

PLO 312, Jalan Tembaga 4,
Pasir Gudang Industrial Estate,
81700 Pasir Gudang,
Johor Darul Takzim, Malaysia
Tel: +607-2538888
Fax: +607-2517881
Telex: MA 60138 TITAN
www.titangroup.com

Product Data

TITANPRO SM669 FOR THIN WALLED, HIGH CLARITY INJECTION MOLDING

CHARACTER	Polypropylene random copolymer. Titanpro SM669 is a clarified grade designed for high transparency articles.
APPLICATIONS	DVD casing, high transparent thin walled containers, storage containers.
ADVANTAGES	Excellent clarity. Good balance of rigidity and impact resistance. Good dimensional stability.
FABRICATION	Equipment - injection molding machine Techniques - standard processing.

<u>TYPICAL RESIN PROPERTIES</u> ^(a)	<u>UNIT</u>	<u>TITANPRO SM669</u>	<u>ASTM METHOD</u> ^(b)
Melt Flow Rate, at 230°C	g/10 min	30	D1238
Density	g/cm ³	0.9	D1505
Tensile Strength at Yield	kg/cm ²	300	D638
Elongation at Yield	%	12	D638
Flexural Modulus	kg/cm ²	13000	D790B
Notched Izod Impact Strength at 23°C	kg-cm/cm	4.5	D256A
Heat Deflection Temperature at 4.6 kg/cm ²	°C	85	D648
Rockwell Hardness	R scale	98	D785A
Water absorption after 24 hours	%	0.02	D570

(a) Values shown are averages and are not to be considered as specifications.

(b) ASTM test methods are latest under the Society's current procedures.

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.